

ALGINATE FOAM COMPOSITIONS

DESCRIPTION OF THE PRIOR ART

U.S. Patent Number 5,718,916 issued to Scherr describes in some detail the background of the use of alginates as well as their application in medical and veterinary medicine; said outline of the background data for the use of alginates as set forth in U.S. Patent Number 5,718,916 in columns 1, 2, and column 3 to line 33, are incorporated herein by reference.

ATTRIBUTES OF THE INVENTION DESCRIBED HEREIN

The U.S. Patent Number 5,718,916 more specifically deals with the preparation of a sponge-like or foam alginate composition which requires lyophilization or freeze drying in order to remove the aqueous component of the composition and so results in a foam product which has certain advantages over fiber-related alginates which are produced by a spinning process.

An advantage of the invention described herein relates to the preparation of foam alginate compositions in which the aqueous portion of the composition can be removed by air-drying or regulated heat drying without the necessity of utilizing an expensive freeze-drying apparatus so significantly reducing the cost of the final product as well as the reduction in time of its preparation.

In the U.S. Patent 5,718,916 for the preparation of alginate foam products, note that the examples cited and many of the claims made, utilize a sequestering agent such as sodium citrate in order to delay the immediate precipitation of calcium alginate when calcium salts are added to a solution of sodium alginate. Since the sequestering agent does not permit too long an extended period of time prior to the alginate being precipitated as the calcium salt, the

examples cited in U.S. Patent 5,718,916 clearly indicate that the composition has to be added to a dish or tray immediately after mixing prior to its being frozen and lyophilized.

It is thus another salient advantage of the invention described herein, that no sequestering agent is required and that the calcium alginate so formed permits a semi-solid gel to be poured into any receptacle even hours after it is formed without the restraints of having to immediately place it into a dish prior to its being dried by a suitable method.

The lack of a restraint of the element of time in preparing the calcium foam alginate composition as described herein makes feasible the adjustment of viscosity of the composition without the necessity to work quickly and freeze the mixture as is made necessary in U.S. Patent No. 5,718,916, prior to its being dried and prepared for use in medical or veterinary applications. Where it might be necessary to effect an adjustment of pH in the alginate foam composition, the operator can also make such adjustments over the period of time necessary without the restraint of time that is inherent in the U.S. Patent Number 5,718,916.

It is generally known in the profession that sodium alginate in aqueous solution is highly sensitive to precipitation by calcium ions and that even as low a concentration of 1 to 100,000 of sodium alginate in aqueous solution, can result in precipitation of calcium alginate in the presence of such solutions as calcium chloride. Since the calcium alginate foam composition prepared herein is highly viscous and would result in a viscosity that may be difficult to layer in a homogenous thin layer on a plate to permit its drying, it was discovered that the addition of ammonia in aqueous solution or ammonium salts would reduce the viscosity of the calcium alginate foam composition and significantly improve the ease with which the layering of the calcium alginate foam composition may be layered. Since, during the drying process, free ammonia is liberated from such a composition which has included the use of a solution of ammonia, liberation of the ammonia will then result in enhanced viscosity and concomitantly

increase strengthening of the foam composition thus prepared by the removal of ammonia during the drying process.

The use of various dressings frequently require that they be very soft and amenable to being draped around fingers, arms, or legs where injury has occurred. Consequently, it is a desirable attribute of such dressings to be highly flexible and amenable to being easily draped without their surface being distorted by the stress of such draping. It has been discovered that the addition of a compound such as sodium tetraborate (borax) results in the calcium alginate foam composition to become highly flexible, have an increased elasticity, and can be readily draped around small circumferences such as a finger without distortion or breakage of the alginate dressing so formed.

Another salient advantage of the invention described herein concerns the feasibility of adding ingredients to the alginate composition, which ingredients may contain properties such as being particulate, having high viscosity, or having or resulting in a rheology which is undesirable in making it feasible for such compositions to be forced through a fine spinneret to produce the alginate fibers as currently practiced in the profession.

The use of desirable particulate matter such as microparticles that can act as time-release particles, aqueous insoluble medicaments, or even the use of intact cells such as yeast cells, blood cells, or human or animal tissue cells, that might be desirable to apply to an open wound may be introduced into the alginate foam composition described herein. As is well known in the profession the pH of the alginate composition may have to be adjusted to be commensurate with the cells that are to be incorporated in the final composition, and such pH adjustment is readily made by those skilled in the art. Such particulate matter and/or aqueous insoluble matter which can be incorporated into the alginate foam composition described in our patent is an attribute not feasible when calcium alginate fibers are prepared by a spinning process.

commercial products of DeRoyal which can be packaged, sterilized, stored, and used directly on a wound at any appropriate time that is desired without the need to use a multiplicity of products and the awkward use of powders and ointments, which then require an additional dressing as described in the above literature. The alginate foam composition described herein serve as a unique matrix for a maltodextrin component.

Having set forth the tenets of the invention contained herein, the following non-limiting examples illustrate various compositions that are inherent in our invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

EXAMPLE 1

Place 4000 ml of deionized water into a plastic container and, with stirring, slowly add 100 grams of Kelco HV brand of sodium alginate. The stirring should be sufficiently vigorous to form a vortex in the water so that the sodium alginate added to the water is directed into the middle of the vortex to ensure a very efficient dispersion of the alginate particles and so increase the rate of solution. The mixture is stirred until all of the sodium alginate has been dissolved.

To 1125 ml of the 2.5% sodium alginate solution prepared as above, add the following ingredients:

15 grams of sodium bicarbonate (Na HCO_3),

75 ml of glycerin,

6.9 ml of the surface active agent polyoxyethylene - polyoxypropylene block polymer (L64, Wyandotte Corp.)

6.9 ml of the surface active agent polyoxyethylenesorbitan monooleate (Tween 80®, Atlas Chemical Industries, Inc.)

After stirring vigorously for approximately ten minutes to ensure that all of the ingredients have been dispersed, add 100 ml of deionized water containing 45 grams of sodium tetraborate

($\text{Na}_2\text{B}_4\text{O}_7 \cdot 10\text{H}_2\text{O}$). After stirring for a few minutes to ensure that the borate solution has been thoroughly dispersed, add 33 ml of ammonium hydroxide (28% NH_3) and 15 grams of polyethylene glycol (average MN CA 1000).

While continuously stirring, slowly add 9 grams of calcium sulfate ($\text{CaSO}_4 \cdot 2\text{H}_2\text{O}$) into the vortex of the alginate solution and then follow with 35 ml of a dilute solution of acetic acid prepared by diluting one part of glacial acetic acid with 2 parts of deionized water.

The diluted acetic acid should be added very slowly with a pipette, again into the vortex of the stirred mixture, and vigorous stirring continued for approximately five minutes.

Following the addition of the acetic acid, the composition will gradually become more viscous. One should now add 1800 ml of deionized water.

The alginate composition thus prepared will contain a considerable amount of foam, which foam will not rise to the surface of the alginate composition, because the viscosity of the final alginate composition is greater than the buoyancy of the foam. When poured onto a plate, such as one made of plastic or metal, the dish may be air-dried or placed into a drying oven on the following schedule of drying:

70° C - 2 hours

60° C - 2 hours

40° C - until dry

Alternately, the alginate composition prepared as above can be poured onto a backing composed of a cotton-rayon mixture or a polyester non-woven backing, so that an amount of the alginate foam mixture penetrates into the fiber and thus when dry, will retain this backing as part of the dried finished dressing.

The U.S. Patent Number 5,674,524 expressed novelty in that prior to said U.S. Patent, the manufacturers of alginate fiber dressings were obliged to recommend that, once the alginate fiber dressing is placed on a wound, then a secondary sterile dressing would have to

be affixed on top of the alginate dressing prior to its being affixed in place with adhesive tapes. The U.S. Patent 5,674,524 resolved the laborious and expensive procedure for alginate dressings to require two separate sterile dressings to be affixed over a wound. This was resolved by utilization of needle punching of the alginate fiber dressing to a backing following the carding operation. It is a unique attribute of the patent described herein, that even needle punching is unnecessary to have the foam alginate composition affixed to a suitable backing of an alginate dressing.

It is thus another salient advantage of the patent described herein that the dried alginate foam composition, when ready to be cut into appropriate sized dressings, packaged, and sterilized ready for use, already has a backing affixed to the alginate foam composition and does not require any additional secondary sterile backing after the alginate composition is placed on an open wound.

EXAMPLE 2

Add 1200 ml of the 2.5% sodium alginate HV brand as prepared above in Example 1 to a 4 liter beaker and with vigorous stirring add the following ingredients in the following order.

40 ml of ammonium hydroxide,

12 ml of Tween 80,

12 ml of L64,

15 grams of sodium bicarbonate,

15 grams of ammonium alginate (Superloid® brand of Kelco Co.)

Add 700 ml of deionized or distilled water and when all of the ingredients have been thoroughly mixed, add 15 grams of sodium tetraborate dissolved in 150 ml of water. With continuous stirring, now slowly add 5 grams of calcium sulfate, 110 ml of glycerin, and

stir for approximately ten minutes. Add 30 ml of dilute acetic acid, the addition of which and the preparation of which are as described in Example 1 above and then the composition may be layered onto a surface or onto a suitable backing, and dried, as described in Example 1 above.

EXAMPLE 3

The zinc salt of bacitracin, having a concentration of 67 IU/mg, is added in an amount of 230 mg to 10 ml of deionized water. Neomycin sulphate powder assaying as 704 mcg neomycin/mg of antibiotic is added to 10 ml of deionized water in an amount of 135 mg. Polymyxin B sulphate containing 8547 units of polymyxin B/mg of powder is added to 10 ml of deionized water in an amount of 22.6 mg. The three separate solutions are stirred until all of the antibiotics have been dissolved.

Antibiotic solutions thus prepared are added to 1200 ml of the 2.5% solution of sodium alginate Kelco brand HV and with continuous and vigorous stirring, the rest of the ingredients as set forth in Example 1 and in the concentrations utilized in Example 1 are added to the alginate-antibiotic composition which may then be spread and dried as described in Example 1 above.

EXAMPLE 4

To 1200 ml of a 2.5% sodium alginate preparation prepared as in Example 1 above, add the following ingredients in the following order:

15 grams of sodium bicarbonate

75 ml of glycerin

6.9 ml of the surface active agent L64

6.9ml of the surface active agent Tween 80

After stirring vigorously for approximately 10 minutes to ensure that all of the ingredients have been dispersed, add 150 ml of deionized water containing 50 grams of sodium

thoroughly dispersed, add 60 ml of ammonium hydroxide and 75 ml of glycerin.

While continuously stirring, slowly add 1 gram of calcium sulfate into the vortex of the solution and then follow with 20 ml of a dilute solution of acetic acid prepared by diluting one part of glacial acetic acid with 2 parts of deionized water.

The diluted acetic acid should be added very slowly with a pipette, again into the vortex of the stirred mixture, and vigorous stirring continued for approximately five minutes.

Following the addition of the acetic acid, the composition will gradually become more viscous; one should continue to add 1000 ml of deionized water. With stirring continued, add 1 gram of a highly hydrophilic preparation called "Drimop"® as manufactured by Multisorb Technologies which is a sodium polyacrylate polymer.

The sodium polyacrylate polymer is highly hydrophilic and therefore, an amount of water would be retained by this product, even after drying in accord with the process set forth in Example 1. The unique value of adding a small amount of a highly hydrophilic preparation results in the retention of bound water to such a hydrophilic agent as the sodium polyacrylate polymer which thus results in a dressing having an amount of moisture which retains a 'cool' touch when the dressing is applied to an open wound. The "Drimop," sodium polyacrylate polymer being highly hydrophilic, also enhances the moisture-absorbing capacity of the dressing when it is applied to an open and/or exudating wound.

The alginate composition thus prepared may be spread on a flat surface and/or onto a suitable backing as described in Example 1 above and air- or oven-dried, again as described in Example 1.

EXAMPLE 5

An alginate foam composition is prepared as described in Example 1 above. The alginate may then be sterilized in a suitable container by ionizing or other suitable sterilizing radiation.

Using established aseptic techniques, a cell suspension is prepared from a culture of human, animal, or microbial cells and are aseptically harvested into a suitable buffered medium.

The cells thus suspended in a medium are then added aseptically to the sterile alginate foam slurry, as prepared above, with slow mixing.

The cell containing alginate foam slurry can then aseptically be layered onto a sterile sheet so that when dried, may be cut into appropriate sizes as required.

EXAMPLE 6

A 600 ml quantity of 2.5% sodium alginate as prepared above in Example 1 is added to a 4 liter container, and to the alginate is added the following ingredients in the following order:

60 ml of glycerin

200 ml of deionized water

6 ml of Tween 80

6 ml of L64 surface active agent

8 grams of sodium bicarbonate

7.5 grams of ammonium alginate

(as sold under the trade name of Superloid® manufactured by Kelco Corporation)

With continued and vigorous stirring, add 1.0 gram of calcium sulphate, and 50 grams of maltodextrin with a dextrose equivalent of 13.0 to 17.0 as prepared by Aldrich Chemical Company, Inc.

The ingredients are stirred vigorously with a stirrer until the composition becomes viscous and to this composition is added 20 ml of ammonium hydroxide and 150 ml of deionized water.

THE **NEW** **YORK** **PUBLIC** **LIBRARY**

[illegible][illegible][illegible][illegible]

THE **NEW** **YORK** **PUBLIC** **LIBRARY**

[illegible][illegible]

monolaurate; Tween 40, polyoxyethylene sorbitan monopalmitate; or Tween 85, polyoxyethylene sorbitan trioleate may be incorporated into the alginate composition without deviating from the novelty of the invention described herein.

Note that in the examples cited herein, the effervescent compound that reacts with the water soluble dilute acetic acid with the resultant evolution of a gas which become entrapped in the formation of the gel foam network is sodium bicarbonate. Other water soluble effervescent compounds may be utilized and other acids may be utilized to produce the evolution of gases which become entrapped in the alginate gel network without deviating from the novelty of the invention described herein. Thus, various water insoluble metal salts that can react with water soluble acids are calcium carbonate, calcium phosphate dibasic, barium carbonate, or zinc carbonate. Examples of suitable acids would include acetic acid, lactic acid, maleic acid, gluconic acid, and ascorbic acids.

Should it be desirable to utilize gases other than carbon dioxide to form the foam that forms the stable hydrogel composition described herein, inert gases such as nitrogen or argon, or other gases may be directly introduced into the alginate composition described in the claims herein as long as the alginate compositions described have a viscosity greater than the buoyancy of the gases entrapped therein. The addition of such other gases will cause the formation of stable hydrogel alginate foam compositions in accord with the novelty of the invention described herein.

Note that in Example 4, we introduce a highly hydrophilic chemical called "DriMop" (sodium polyacrylate polymer) for the purpose of enhancing the moisture-absorbing capacity of the dressing. Other hydrophilic compounds may be utilized in order to achieve an enhanced moisture absorption of the dressing without deviating from the novelty of the invention described herein.